



Z BOND® 6S

Sanitary & Tile Silicone Sealant

DESCRIPTION

Z Bond® 6S is a one component, non-flowing, NEUTRAL cure, MID modulus silicone sealant. It cures by absorption of atmospheric moisture to form a flexible and durable elastomeric sealant.

SPECIAL FEATURES

Z Bond® 6S contains an effective fungicide, to reduce the growth of mould and mildew.

Because it is a neutral curing system, it is more pleasant to work with particularly in a confined space. It also offers excellent adhesion to powder coated metal.

The thixotropic nature of this product ensures that it will not slump in typical construction joints.

Meets the standard of NZFSA – C82 (Titanium / off white).

TYPICAL USES

- Bathrooms,
- Fibreglass Spa Units,
- Shower screens,
- Ceramic tiles,
- Tiles and grout areas. (for Granite, Marble and some porous stones, use / refer to Bostik 5CLM data sheet)
- Around edges of kitchen bench tops,
- Edges of splash backs (*Not to be used on the back of splash backs, refer to Bostik V:60)
- Cool Rooms.

PART NUMBER & COLOURS - 14

662000	Translucent
662010	White
326437	Gloss White
313521	Titanium / Off White
661990	Almond Ivory
326445	Ceramic Ivory

326402	Mid Grey
327166	Sandstone
328421	Beige Sand
283975	Pewter
292885	Charcoal
283967	Silver Ash
341223	Antique White
341231	Taupe

(Other colours can be made for projects, subject to volumes).

PACKAGING

The standard packaging for Z Bond® 6S is 300 & 410g polyethylene cartridges.

Carton size -15 cartridges per box.

Please contact your local agent - Waterproofing Warehouse - for details of minimum order size, lead-time and dispensing methods.

ONE PART SYSTEM

Being a one-part sealant Z Bond® 6S offers the confidences of consistent even cure. It also improves operator productivity, as time is not lost mixing the product, it is easy to use in difficult locations, and application is out of a standard cartridge gun.

LONG LIFE RELIABILITY

Z BOND® 6S has excellent natural ageing stability. It will maintain its elastomeric joint sealant properties permanently, even under harsh conditions and temperature extremes.

CHARACTERISTICS

SYSTEM PROPERTIES		
Property	Mean Result Achieved	Test Method
Skin Time	8 – 10 Minutes	BS 5889
Tack Free Time	30 Minutes	ASTM C679
Tooling Time	10 Minutes	ASTM C679
Sag or Slump	Nil	BS 5889

CURED PROPERTIES		
Property	Mean Result Achieved	Test Method
Shore A Hardness	17 – 22	ASTM C 661
Modulus at 100% Elongation	0.4 MPa	ASTM D 412
Tensile Strength	1.1 – 1.5 MPa	ASTM D 412
Elongation at Rupture	630 – 670%	ASTM D 412
Peel Strength after UV through Glass	50N/25mm	BS 5889
Dynamic Movement Capacity	± 25%	ASTM C 920
Accelerated Aging and Weathering	Excellent	ASTM C 792

TEMPERATURE		
	Minimum	Maximum
Application Temperature	-10°C	+40°C
Service Temperature	-50°C	+150°C

Applications of the sealant at +5°C - +35°C is permissible provided the surface to receive the silicone is dry and free of frost. The maximum service temperature listed is for transient temperatures; the silicone sealant will deteriorate if subjected to these temperatures on a continuous basis.

SEALANT APPLICATION JOINT DESIGN

The sealant must be capable of withstanding the expected joint movement. To calculate the joint width, establish the expected movement (expansion, contraction and shear movement) that the joint is required to withstand. The dynamic movement capability of Z BOND® 6S is ± 25.

The joint design must avoid three-sided adhesion. The sealant depth for a weatherseal is normally half the joint width. The minimum acceptable joint depth is 6mm; therefore, if the required joint width is 6mm the depth is also 6mm.

BACK UP MATERIAL

Use a closed cell polyethylene-backing rod, 25% larger than the joint width, to control the depth of the joint.

COMPATIBILITY WITH ADJACENT SUBSTRATES

Silicones are not always compatible with plasticised sealants, such as butyls.

Also some backing rods and glazing tapes contain bitumen or other agents that are incompatible with the silicone.

The incompatibility may cause discolouration, poor sealant cure or long term degradation of the sealant. Always carry out compatibility tests where contact with potentially incompatible materials occurs.

APPLICATION

Always ensure that the surfaces to be sealed are dry and free from oil, dirt and grease.

Use the two-wipe process for impervious substrates. Ensure the cloths are clean and changed frequently, and use a suitable cleaner/solvent such as Z Bond® R-40, or IPA.

When extruding the sealant cut the nozzle to the desired width, cut the tip off the cartridge, and apply the sealant firmly to ensure good contact between the sealant and the substrate.

Before the sealant has skinned, tool it off to ensure a good finish, and to improve the wetting out of the sealant to the substrate. To achieve satisfactory adhesion a primer may be required for some substrates. Consult Bostik or your distributor for more information.

CURING

Z BOND® 6S cures by absorbing atmospheric moisture, it will skin over in 8 – 10 minutes and cure to a depth of 7mm in 7 days.

DESIGN SUPPORT

Because of the importance of Surface Preparation, Sealant Application and Joint Design Bostik Australia provide specific Data Sheets on these topics. These data sheets are available Free of Charge, and we strongly recommend that you consult these sheets before commencing application of the sealant.

We will also review shop or working details, test substrates, and associated material for compatibility and adhesion, and make sealant recommendations when requested.

STORAGE AND SHELF LIFE

Always store the sealant in a cool dry place. Ideal storage temperature is not more than 25°C. Prolonged storage at high temperatures may affect shelf life and ultimate performance. The shelf life of Z BOND 6S is 12 months from the date of manufacture when stored below 25°C and below 50% relative humidity.

LIMITATIONS

Z BOND 6-S is NOT suitable for the following applications:

- As the sealant requires atmospheric humidity to cure, it will not cure in totally confined spaces where it does not have access to atmospheric humidity.
- Aquariums
- Adhering Mirrors
- Structural Glazing
- Under Water Applications (including swimming pools – subject to substrate).
- N.B. This product is suitable for some applications where the sealant is in contact with water for extended periods. Please contact Bostik Australia Pty Ltd. to confirm your design details before commencing.
- Below Grade Applications
- All stone's (We recommend the completion of a stain testing program before using any sealant on stone)
- Horizontal walkways.
- Do not clean or treat the sealant with materials, cleaning agents or solvents, that may affect or discolour the sealant, particularly during product curing.

THIS SILICONE IS NOT PAINTABLE

If there is, a requirement to paint the sealant our recommendation is to use our Z Bond® 400P paintable silicone sealant or Z Bond® Gap Filler acrylic sealant products.

Follow both the sealant and paint manufacturers painting instructions carefully, when painting sealants.

2.2 HEALTH AND SAFETY

Full product safety information required for safe use is not included in this data sheet.

Before handling, read the separate Material Safety Data Sheet (MSDS) and packaging for safe use.

In case of product emergency refer to product labelling or MSDS and contact phone numbers.

A copy of the product MSDS is available from Bostik or its distributors.

IMPORTANT NOTICE FOR USERS

Suggestion for use should not be taken as an inducement to infringe any particular patent.

*Z Bond® is a registered trademark of Bostik Australia.

The representations and recommendations regarding the products are based on tests which we believe to be reliable. However, no guarantee of their accuracy can be made because of the great range of field conditions and variations encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with a limited warranty only, and on the condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik Australia Pty Ltd be liable to anyone except for replacement of the products or refund of the purchase price.

PT BOSTIK INDONESIA

Atrium Setiabudi Building, Jl. HR Rasuna Said Kav. 62,
Jakarta 12920, Indonesia

BOSTIK HOTLINE

Layanan Bantuan **+62 21 521 0404**

